

TECHNICAL DATA

AMBERIZER
Typical Properties and Application Procedures

4X0200

PRODUCT DESCRIPTION

Basic's Amberizer allows you to achieve the rich, traditional look of oil with all the conveniences of a water based finish. *Amberizer* can be added directly to any of Basic's water based sealers or finishes to give the appearance of an aged oil-modified urethane.

TYPICAL PROPERTIES

ColorDark Amber
Solids ContentN/A
VOC0 grams/liter (0.0
pounds/gallon) less water
Flash Point ... Greater than 200° F
Freeze/Thaw Stability ...Stable. Thaw completely
before using.
Clean Up ... Water

PACKAGING

1 US quart plastic container (6 per case)

INSTRUCTIONS FOR USE

Loosen cap on measuring reservoir. Squeeze bottle to fill reservoir to appropriate measurement. To prevent spillage, grip the top of the bottle to pour product out of reservoir. Excessive product can be poured out if you squeeze the container while pouring.

1. Rock product container several times before opening.
2. Pour product into a clean, dry plastic pour can. Add 1-2 ounces of *Amberizer* to one gallon of Basic's water based sealers or finishes. Mix thoroughly to achieve consistent color. (If using a catalyzed product, slowly add Basic 2X Catalyst or XL Catalyst). See product technical data sheet.
3. **When coating over bare wood, apply first coat of "clear" sealer/finish, followed by a coat of "Amberized" sealer/finish. Use additional "Amberized" coats to build color.**

Always maintain a consistent film during application so that color is consistent across the entire floor. Inconsistent film thickness may result in light or dark spots on the floor.

OBLIGATION OF MANUFACTURER

The following is made in lieu of warranties, expressed or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for an injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, the user shall determine the suitability of the product for the intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers of seller and manufacturer.